NUROIL TRADING
Sharjah, United Arab Emirates

4 cSt Base Oil

Group III | Group III base oil

TYPICAL SPECIFICATION

Characteristic	Units	4 cSt	Test method
Kinematic viscosity at 100°C	cSt	**4.1 - 4.4**	ASTM D-445
Kinematic viscosity at 40°C	cSt	**19.0 - 20.0**	ASTM D-445
Viscosity index (VI)	-	**min. 120**	ASTM D-2270
Flash Point	°C	**min. 220**	ASTM D-92
Sulphur Content	%Wt	**0.001**	ASTM D-2622
Pour Point	°C	**max. -12**	ASTM D-97

NOTICE

Values are published catalogue values. Confirm the applicable specification for the offered origin before ordering. Base oil is a base stock; finished lubricant performance depends on the additive system and formulation.