

**BITUMEN AC-20**

(Viscosity Grade)

**TYPICAL PROPERTIES**

<b>Property</b>	<b>Units</b>	<b>AC-20</b>	<b>Test Methods</b>
Viscosity, 140°F (60°C)	P	2000± 400	ASTM D-2171
Viscosity, 275°F (135°C), Min	cSt	210	ASTM D-2171
Penetration, 77°F (25°C), 100g, 5sec, Min	0.1MM	40	ASTM D-5
Flash point, Cleveland open cup, Min	°C	450(232)	ASTM D-92
Solubility in trichloroethylene, Min	%Wt	99	ASTM D-2042
<b>Tests on residue from thin-film oven test:</b>			
- Viscosity, 140°F (60°C), Max	P	10,000	ASTM D-2171
- Ductility, 77°F (25°C), 5cm/min, Min	CM	20	ASTM D-113

For further information, please contact:

**Nuroil Trading FZE**

Sharjah, United Arab Emirates.

Email : [info@nuroil.com](mailto:info@nuroil.com)

Phone : +971 (55) 840 5476