

**BITUMEN AC-40**

(Viscosity Grade)

TYPICAL PROPERTIES

Property	Units	AC-40	Test Methods
Viscosity, 140°F (60°C)	P	4000± 800	ASTM D-2171
Viscosity, 275°F (135°C), Min	cSt	300	ASTM D-2171
Penetration, 77°F (25°C), 100g, 5sec, Min	0.1MM	20	ASTM D-5
Flash point, Cleveland open cup, Min	°C	450(232)	ASTM D-92
Solubility in trichloroethylene, Min	%Wt	99	ASTM D-2042
Tests on residue from thin-film oven test:			
- Viscosity, 140°F (60°C), Max	P	20,000	ASTM D-2171
- Ductility, 77°F (25°C), 5cm/min, Min	CM	10	ASTM D-113

For further information, please contact:

Nuroil Trading FZE

Sharjah, United Arab Emirates.

Email : info@nuroil.com

Phone : +971 (55) 840 5476