

# BITUMEN 80/100

(Penetration Grade)

## TYPICAL PROPERTIES

PROPERTY	UNIT	80/100	TEST METHODS
Specific Gravity @25°C	-	1.01-1.05	ASTM D-70
Penetration @25°C, 100gm, 5sec	0.1MM	80/100	ASTM D-5
Softening Point, Ring & Ball	°C	45-52	ASTM D-36
Ductility @25°C, after TFOT, Min	CM	100	ASTM D-113
Loss on Heating, Max	%Wt	0.5	ASTM D-6
Drop in Penetration after Heating, Max	%	20	ASTM D-6 & D-5
Flash Point Cleveland open cup, Min	°C	232	ASTM D-92
Solubility in CS <sub>2</sub> , Min	%Wt	99.5	ASTM D-4
Organic Matter Insoluble in CS <sub>2</sub> , Max	%Wt	0.5	ASTM D-4
Sport Test	-	Negative	*A.A.S.H.O.T.102

**Penetration Grade Bitumen** is commonly used in road construction, surfacing and some industrial applications. Additional processing of this type of Bitumen yields various grades of Bitumen products. The Penetration Test determines the hardness of Bitumen by measuring the depth ( in tenths of a mm) to which a standard, and loaded needle will vertically penetrate in 5 seconds, a sample of Bitumen maintained at a temperature of 25°C. Hence the softer the bitumen, the greater will be its number of penetration units. Bitumen Grade 80/100 is commonly used to manufacture Asphalt Mixes, Cut-back Bitumen, Bitumen Emulsions and Modified Bitumen.

**Quality:** All Bitumen supplied is of the highest quality and fully compliant with ASTM and AASHTO, equivalent EN and BS International Standards and Test Methods. SGS Quality Testing and Analysis certification of the Bitumen products inspected when requested, will be compliant with Product Specifications and International Standards. Quality assured manufacturing. Equivalent to BS EN 12591 and BS EN 13924.

**Packaging:** New steel drums, reconditioned steel drums or eco-friendly poly bags. Weatherproof packaging.

**Storage and Handling Recommendations:** Store in unopened containers. Storage temperature limits 1°C - 50°C. For normal operations, such as blending and transferring liquid bitumen, temperatures of 10°C - 40°C above the minimum pumping temperature are recommended.

### Recommended Application Temperatures:

<b>Storing</b>	: 120°C - 150°C.
<b>Mixing</b>	: 130°C - 150°C.
<b>Compacting</b>	: 120°C - 140°C.

For further information, please contact:

### Nuroil Trading FZE

Sharjah, United Arab Emirates.

Email : info@nuroil.com

Phone : +971 (55) 840 5476