

**BITUMEN VG-40**

(Viscosity Grade)

**TYPICAL PROPERTIES**

<b>Property</b>	<b>Units</b>	<b>VG-40</b>	<b>Test Methods</b>
Penetration at 25°C, 100g, 5sec, Min	0.1MM	35	IS 1203
Absolute viscosity at 60°C	P	3200-4800	IS 1206 (Part 2)
Kinematic viscosity at 135°C, Min	cSt	400	IS 1206 (Part 3)
Flash point (Cleveland open cup), Min	°C	220	IS 1448 [P : 69]
Solubility in trichloroethylene, Min	%Wt	99	IS 1216
Softening point (R&B), Min	°C	50	IS 1205
<b>Tests on residue from thin film oven test:</b>			
- Viscosity ratio at 60°C, Max		4	IS 1206 (Part 2)
- Ductility at 25°C, Min	CM	25	IS 1208

For further information, please contact:

**Nuroil Trading FZE**

Sharjah, United Arab Emirates.

Email : [info@nuroil.com](mailto:info@nuroil.com)

Phone : +971 (55) 840 5476