



Oxidized Bitumen 95/25

(Blown Bitumen)

PRODUCT DATA SHEET

Oxidized Bitumen 95/25 (or Blown Bitumen 95/25) is a hard, thermally stable grade of bitumen produced by passing air through bitumen at high temperatures. This oxidation process modifies its properties, giving it a higher softening point and lower penetration value, making it resistant to extreme weather and chemical exposure.

CHARACTERISTICS	UNIT	LIMITS	TEST METHODS
Penetration @25°C (77°F), 100gm, 5sec	0.1MM	20-30	ASTM D5
Softening Point °C	°C	90-100	ASTM D36
Ductility @25°C, 5 cm/min	CM	Min. 1.5	ASTM D113
Solubility in CS ₂	%Wt	Min. 99	ASTM D4
Flash Point Cleveland open cup	°C	Min. 260	ASTM D92
Specific Gravity at 25°C	-	1.00-1.05	ASTM D70

After Rolling Thin-Film Oven Test (RTFO)

Loss on Heating	%Wt	0.2	ASTM D6
-----------------	-----	-----	---------

Quality:

The quality of the bitumen is assured for every delivery with arrangement of international inspector to check quality and controlling the production by Quality Control and also by batch test report before shipping.

Application:

Oxidized bitumen 85/25 is widely used in various industrial applications due to its durability and resistance to temperature fluctuations. Its primary uses include waterproofing membranes and roofing felts, road construction for surfacing and crack sealing, and as a protective coating for metal pipelines to prevent corrosion. It also serves as an electrical insulator for cables, an adhesive in flooring and tiles, and a damp-proofing agent for building foundations.

Health & Safety:

Bitumen is unlikely to present any significant health or safety hazard when properly used in the recommended application, provided good standards of industrial and personal hygiene are maintained.

Packaging:

New steel drums, reconditioned steel drums or eco-friendly Weatherproof packaging in poly bags, Kraft bag

Steel Drums : 180Kg, 200Kg

Jumbo Bag : 1000Kg

Others : 25kg Kraft/PP Bag, Metal Pails, Carton Box

Code Approvals/Compliance:

Meets BS EN 13304-2009

Learn More

www.nuroil.com

For further information, please contact:

Nuroil Trading FZE

Email : info@nuroil.com

Phone : +971 55 8405476

Disclaimer: The information contained herein is based on our current knowledge of the underlying data and is intended to describe the product for the purpose of health, safety and environmental requirements only. No warranty or guarantee is expressed or implied regarding the accuracy of these data or the results to be obtained from the use of the product.